

# **DECORATIVE WATER-BASED INTERIOR PRODUCT GROUP**

# **Tempo Silicone Silk Interior Paint**

#### PRODUCT DESCRIPTION

Silicone-modified, wipe-clean, silky-matte textured, decorative, top-coat, water-based, interior paint.

#### **FEATURES**

High coverage and wipe-clean. Integrates with the application surface thanks to its high adherence. Features a high level of breathability. Causes no cracking, blistering or flaking if applied correctly. No disturbing odor due its water-based formula and environment-friendly.

#### **APPLICATION SURFACES**

Can be applied reliably on concrete, plaster, precast concrete panel, OSB, previously painted surfaces, glass textile, paintable wall papers after applying a proper primer.

# **APPLICATION**

Ensure the application surface is smooth, dry, clean, solid, and able to bear the paint. Remove any stain, dust, mold grease and loose layers. Perform required surface corrections, prime with a proper primer and then paint. Comply with defined setting periods on concrete, exposed concrete and new plastered surfaces (28 days). Sand the surfaces using fine grained emery paper before starting to apply primer on previously painted surfaces (water- and solvent-based). Apply Tempo Transition Primer after sanding the previously painted surfaces in case they were painted with solvent-based paints. Use Tempo Universal Primer on new plastered interior surfaces which will be painted for the first time. Then, apply Tempo Silicone Silk Interior Paint.

Apply Tempo Binder thinned in a ratio of 1:7 on absorbing and high dust generating surfaces like plaster, lime and aerated concrete in a single coat without combing and finishing in a way that will prevent formation of a glassy thin film layer on the surface. (See Tempo Binder label) Ensure that ambient and surface temperatures are between +5 °C and 30 °C during application. Apply using a brush, roller or spray gun. Our products should be applied on substructure surfaces that are built in line with 30.06.2007 dated General Construction Specifications No. 26568.

# **Airless Spraying:**

Pressure: 140 bar

Nozzle Angle: 50°

Nozzle Size (inch): 0.019"

Thinning (Water): 5% (Volume)



# **THINNING RATIO**

Recommended to be applied in two coats after diluting by 15-20% with clean water.

Recommended to be applied in a single coat provided that sufficient film thickness is achieved after thinning by 5% with clean water in airless spraying.

# DRYING TIME (at 20 °C, 65% RH):

First drying: 30-60 minutes

Second coat application: 4-5 hours

Final drying: 24 hours (drying time can increase at higher relative humidity and lower temperatures).

#### **CONSUMPTION**

 $22 \text{ m}^2$  area can be painted in a single coat with 1 Liter. It can be change due to surface kind, thinning ratio , weather conditions and painter. Perform a controlled sample run to estimate the precise consumption.

# **STORAGE**

May be stored for 3 years in its unopened packaging in a cool and dry environment protected against frost and direct sunlight.

# **PACKAGING**

15 L, 7.5 L, 2.5 L

# **WARNING WORD**

Caution

# **HAZARD PHRASE**

H317 May cause an allergic skin reaction.

### **PRECAUTIONARY PHRASES**

P101 If medical advice is needed, have product container or label at hand.

P102 Keep out of reach of children.

P103 Read label before use.

P261 Avoid breathing dust/fume/gas/mist/vapors/spray.

P280 Wear protective gloves/protective clothing/eye protection/face protection.

P321 Specific treatment required (see label).

P363 Wash contaminated clothing before reuse.

P333+P313 If skin irritation or a rash occurs: Get medical advice/attention.

P501 Dispose of contents/container in accordance with local, regional, national and international regulations.





Complies with TS 5808/2012.



Complies with the G communique.

TSE

Gloss: Semi-Matte

Granule Size: Fine

Coverage Strength: Class 2 (7 m<sup>2</sup>/L)

Wet Scrub Resistance: Class 2

# Pose No.

15.540.1206, 15.540.1217, 15.540.1218, 15.540.1219

# Rate No.

10.300.1002

This technical sheet is prepared based on laboratory data at normal conditions, consult technical personnel for details that are not provided above. Otherwise, the manufacturing company cannot be held responsible for failures that may arise due to lack of knowledge. Our company reserves the right to change this information.

This product is manufactured by Betek A.Ş. with certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, TS ISO/IEC 27001.

Rev1 2021